

UltraLite® MULTI UV 5M/40-20

UltraLite® MULTIWALL UV 5M/40-20 is a polycarbonate sheet of 40 mm thickness, with an M-structure for enhanced stiffness. It combines good load bearing properties, excellent thermal insulation, light transmission and excellent weather resistance. The sheet is lightweight, impact resistant and easy to install.

is ideal for
flat glazing applications • conservatories • industrial glazing, sports halls
• partition walls • skylights, north light glazing • Green building roofing, cladding (facades)

The sheets are produced with a coextruded UV-protective layer, which is homogeneously fused with the sheet material. This UV-protected side must be installed facing upwards/outwards. It provides ULTRALITE® multi UV with a highly effective protection against weathering, guaranteed for 10 years.

Technical data

	Typical Values	
Area weight	4.2 kg/m ²	
Width	2100 mm	
Length	11800 mm	
Light transmission TD65 (UV Absorbing)	Clear	35±3%
Total energy transmission g	Clear	47%
Shading coefficient	Clear	0.54(calculated)
Heat transfer coefficient Ug	Vertical application	1.1W/ m ² K
	Horizontal application	1.1W/ m ² K
Coefficient of thermal expansion α	0.065 mm/m°C	
Possible expansion due to heat and moisture	3mm/m	
Maximum services temperature without load	120°C	
Fire rating		
Europe	Clear	B-S1-d0 (EN13501-1)
Germany	Clear	B2 (DIN 4102)
UK	Clear	1Y (B476 , part 7)
Weighted sound reduction index	19dB	

Product data sheet 2021


ULTRALITE® MULTI UV 5M/40-20

MULTI WALL POLYCARBONATE SHEET

*Silent, Safe, Sustainable PC
Sheets – Make in India*

Advantages:

- Extremely heat insulating
- High stiffness
- Good load bearing capacity
- ISI approved



Contact details:

Email: quality.sheet@saraswati-group.com
Saraswati Plastotech India Pvt Ltd
Lane 4, Phase 1, SIDCO Industrial
Complex, Bari Brahmana,
Jammu 181133
<http://saraswatiplastotech.com/>

The manner in which you use and the purpose to which you put and utilize our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance, information and recommendations to determine to your own satisfaction whether our products, technical assistance and information are suitable for your intended uses and applications. This application-specific analysis must at least include testing to determine suitability from a technical as well as health, safety, and environmental standpoint. Such testing has not necessarily been done by SPT. Unless we otherwise agree in writing, all products are sold strictly pursuant to the terms of our standard conditions of sale which are available upon request. All information and technical assistance is given without warranty or guarantee and is subject to change without notice. It is expressly understood and agreed that you assume and hereby expressly release us from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance, and information. Any statement or recommendation not contained herein is unauthorized and shall not bind us. Nothing herein shall be construed as a recommendation to use any product in conflict with any claim of any patent relative to any material or its use. No license is implied or in fact granted under the claims of any patent.